

SAF-RC-134
400 Area D4 Waste Characterization
Sampling – Other Solid In-Process
FINAL DATA PACKAGE

COMPLETE COPY OF DATA PACKAGE TO:

No Distribution Required

COMMENTS:

SDG D111153 SAF-RC-134

Rad only

Chem only

Rad & Chem

Complete

Partial

Sample Location/Waste Site: 4814






ALS
Laboratory
Group
formerly
DataChem

Cover

Page 1 of 6



Report Identification Number: D1111153
 Subcontract Number: S003827A00
 Name of Industrial Hygienist: Gwen Whatley / Debbie Gothard / Ken Way
 Laboratory Identification Number: DCHM *RC-134 JD 5/3/11*
 SAF#: ~~RC-001~~ / RC-134-10
 Sample Receipt Date: 04/21/2011

Sample Information

Sample Date	Customer Sample Number	Laboratory Sample Number	Method	Analytical Batch Identification	Sample Matrix
04/19/2011	J1H1R1	1111153001	NIOSH 9002	65564	Bulk
04/19/2011	J1H1R2	1111153002	NIOSH 9002	65564	Bulk
04/19/2011	J1H1R3	1111153003	NIOSH 9002	65564	Bulk
04/19/2011	J1H1R4	1111153004	NIOSH 9002	65564	Bulk
04/19/2011	J1H1R5	1111153005	NIOSH 9002	65564	Bulk

I certify that this electronic image and all hardcopies produced from this image accurately represent the data and are in compliance with the contract specific requirements, both technically and for completeness, other than the conditions detailed above or in the sample data package narrative. Release, by submission through email, the data contained in this electronic image and the computer-readable EDD (as applicable), has been authorized by the laboratory Manager or the Manager's designee.

Name: Peter P. Steen
 Title: Chemist
 Date: May 02, 2011



Report Identification Number: D1111153
Subcontract Number: S003827A00
Name of Industrial Hygienist: Gwen Whatley / Debbie Gothard / Ken Way
Laboratory Identification Number: DCHM
SAF#: RC-001 / RC-134-10
Sample Receipt Date: 04/21/2011

General Workorder Information: There are two samples in workorder 1111143, four samples in workorder 1111152, five samples in workorder 1111153, five samples in workorder 1111154, and eight samples in workorder 1111156 which were analyzed for asbestos in bulk material. No problems were encountered with the receipt of this sample.

Method Summary: All samples were examined for homogeneity. Non-homogeneous samples were ground to ensure homogeneity. Distinct layers were analyzed separately. The samples were prepared and examined for asbestos fibers utilizing the procedures outlined in NIOSH method 9002 (4th edition). A polarizing light microscope equipped with a 10x and a 16x eyepiece was used for the analysis. The area percentage of asbestos was estimated microscopically by a visual estimation of the fibers with a length-to-width aspect ratio of 3:1 or greater. If present, asbestos identities were confirmed with the appropriate refractive index oils applying dispersion staining techniques.

Sample Preparation: All samples were prepared in accordance with NIOSH method 9002 (4th edition).

Initial and Continuing Calibration Verification Analysis: N/A

Initial and Continuing Calibration Blank Analysis: N/A

Method Blank Analysis: N/A

Dilution(s): N/A.

Laboratory Control Sample and Duplicate Analysis: One Laboratory Control Sample (LCS) was prepared and analyzed with the sample batch. The results were within the control limit of +/- one reporting range.

Replicate Analysis: Two samples were replicated with this analysis batch.

Flagging Codes: None

Nonconformance/Corrective Action Report (NC/CAR): N/A



Sample Calculation: Sample results are reported by a visual estimation of the area percentage of asbestos. If necessary, a gravimetric ashing procedure may be used to remove certain non-asbestos material from the sample; a percentage calculation is used to correct for the removal of the non-asbestos material.

Miscellaneous Comments:

- 111143001: Black, compacted/fibrous pipe coating.
- 111143002: Black, compacted/fibrous pipe coating.
- 111152001: Yellow, fibrous fiberglass insulation.
- 111152002: Yellow, fibrous fiberglass insulation.
- 111152003: Yellow, fibrous fiberglass insulation.
- 111152004: Gray, rubbery caulk.
- 111153001: Yellow, fibrous fiberglass insulation.
- 111153002: Yellow, fibrous fiberglass insulation.
- 111153003: Gray, hardened caulk.
- 111153004: Gray, hardened caulk.
- 111153005: Gray, rubbery caulk.
- 111154001: Yellow, fibrous fiberglass insulation.
- 111154002: Yellow, fibrous fiberglass insulation.
- 111154003: Brownish, rubbery caulk.
- 111154004: Gray, rubbery caulk.
- 111154005: Gray, rubbery caulk.
- 111156001: Yellow, fibrous fiberglass insulation.
- 111156002: Yellow, fibrous fiberglass insulation.
- 111156003: Yellow, fibrous fiberglass insulation.
- 111156004: Yellowish, foamy material.
- 111156005: White/brown, powdery/papery drywall.
- 111156006: Whitish, rubbery caulk.
- 111156007: Gray, hardened/fibrous material.
- 111156008: Whitish, rubbery caulk.



Results

Report Identification Number: D1111153
 Subcontract Number: S003827A00
 Name of Industrial Hygienist: Gwen Whatley / Debbie Gothard / Ken Way
 Laboratory Identification Number: DCHM
 SAF#: RC-001 / RC-134-10
 Sample Receipt Date: 04/21/2011

Customer Sample Number	Laboratory Sample Number	Date Analyzed	Chrysotile %	Amosite %	Crocidolite %
J1H1R1	1111153001	05/02/2011	<1 U	<1 U	<1 U
J1H1R2	1111153002	05/02/2011	<1 U	<1 U	<1 U
J1H1R3	1111153003	05/02/2011	<1 U	<1 U	<1 U
J1H1R4	1111153004	05/02/2011	<1 U	<1 U	<1 U
J1H1R5	1111153005	05/02/2011	<1 U	<1 U	<1 U
Required Detection Limit (RDL)			1	1	1

Customer Sample Number	Laboratory Sample Number	Date Analyzed	Actinolite/Tremolite %	Anthophyllite %
J1H1R1	1111153001	05/02/2011	<1 U	<1 U
J1H1R2	1111153002	05/02/2011	<1 U	<1 U
J1H1R3	1111153003	05/02/2011	<1 U	<1 U
J1H1R4	1111153004	05/02/2011	<1 U	<1 U
J1H1R5	1111153005	05/02/2011	<1 U	<1 U
Required Detection Limit (RDL)			1	1

U - Parameter not detected above LOD
 J - Parameter between LOD and RDL
 ** - Not provided or unable to calculate
 NA - Not Applicable



QC Summary

Report Identification Number: D1111153
 Subcontract Number: S003827A00
 Name of Industrial Hygienist: Gwen Whatley / Debbie Gothard / Ken Way
 Laboratory Identification Number: DCHM
 SAF: RC-001 / RC-134-10
 Sample Receipt Date: 04/21/2011

Batch ID: 65564

QC Sample ID	QC Type	Analyte	Units	Result	Target
QC107865	LCS	Anthophyllite	%	10	7.5
QC107865	LCSD	Anthophyllite	%	20	7.5
QC107865	LCS	Chrysotile	%	ND	ND
QC107865	LCSD	Chrysotile	%	ND	ND

MB - Method Blank

LCS - Laboratory Control Sample

LCSD - Laboratory Control Sample Duplicate

MS - Matrix Spike

MSD - Matrix Spike Duplicate

LD - Laboratory Duplicate

NA - Not Applicable

ND - Parameter not detected above LOD

LCS, LCSD Percent Rec. = (Result / Target) * 100.0

MS, MSD Percent Rec. = ((Result - Parent) / Target) * 100.0

LCS, LCSD Relative Percent Diff. = ((|LCS - LCSD|) / ((LCS + LCSD)/2.0)) * 100.

MS, MSD Relative Percent Diff. = ((|MS - MSD|) / ((MS + MSD)/2.0)) * 100.

LD Relative Percent Diff. = ((|Parent - LD|) / ((Parent + LD)/2.0)) * 100

