

SAF-RC-040
300 Area D&D Waste Characterization
Sampling - Other Solid
FINAL DATA PACKAGE

COMPLETE COPY OF DATA PACKAGE TO:

Mike Stankovich

L1-01

KW 12/27/07
INITIAL/DATE

RECEIVED
JAN 03 2008
EDMC

COMMENTS:

SDG 07-A-6729

SAF-RC-040

Rad only

Chem only

Rad & Chem

Complete

Partial

Sample Location/Waste Site: 300 Area 309 Bldg.



**DATA
CHEM**
LABORATORIES, INC.

12/21/07
Page 1 of 8

SUBMITTED TO:

Joan Kessner
Washington Closure Hanford
2620 Fermi Avenue, MSIN H4-21
Richland, WA 99354




REFERENCE DATA:

| | |
|----------------------|---------------------------|
| Client Sample No.: | J162V3 through J162V9 |
| P.O. No.: | Not Available |
| Sample Location: | 309 |
| Sample Type: | Bulk |
| Method Reference: | EPA-600/R-93/116 |
| DCL Set ID No.: | 07-A-6729 |
| DCL Sample ID No.: | 07-39413 through 07-39452 |
| Sample Receipt Date: | 11/27/07 |
| Analysis Date: | 12/21/07 |

We certify that the following samples were prepared and analyzed by Polarized Light Microscopy for asbestos and other fibrous constituents using EPA-600/R-93/116. The samples were acceptable upon receipt except where noted. The samples were examined under a stereomicroscope in a laboratory fume hood for general composition and phase separation. If needed, portions of the sample were removed and ground with a mortar and pestle before being mounted on a glass microscope slide. Mountings of representative portions of the material are prepared in one or more appropriate refractive index liquids (1.550, 1.605, 1.680) and examined by Polarized Light Microscopy*. Estimates of concentration are made on an area basis. The results of the analysis apply only to the materials analyzed and are summarized on the attached bulk asbestos analysis data sheets. DataChem Laboratories will dispose of all bulk samples after 60 days unless other arrangements are made.


Shawn Smythe
Analyst


for Anna Marie Ristich
Reviewer

*Floor tiles, decorative paints, joint compounds, and cement materials require additional treatment in order to evaluate the concentration of small asbestos fibers bound in the material. Some samples may contain fibers that are not visible by PLM and can only be detected by electron microscopy techniques. Floor tiles are analyzed as homogeneous materials if insufficient mastic is present or if phases have been cross contaminated.

DataChem Laboratories NVLAP Lab ID: 101917. Laboratory accreditation by the National Institute of Standards and Technology does not in any way constitute approval or endorsement by NVLAP, NIST, or any agency of the federal government..

CINCINNATI OFFICE
4388 GLENDALE-MILFORD ROAD
CINCINNATI, OHIO 45242-3708
513 733-5336, FAX 513 733-5347

WEST COAST OFFICE
11 SANTA YORMA COURT
NOVATO, CALIFORNIA 94945
800 280-8071, FAX 415 893-9469

DataChem Laboratories
Polarized Light Microscopy
Asbestos Analytical Report

Client: Washington Closure Hanford
 Location: 309
 Set ID: 07-A-6729

| Client Sample ID: | J162V3 | J162V4 | J162V5 | J162V6 | J162V7 |
|--------------------------------|------------|------------|------------|------------------------|------------|
| DCL Sample ID: | 07-39413 | 07-39414 | 07-39415 | 07-39416 | 07-39417 |
| Macroscopic Examination | | | | | |
| Accepted/Rejected: | Accepted | Accepted | Accepted | Accepted | Accepted |
| Homogeneity: | Homog. | Homog. | Homog. | Layered Inseparable | Homog. |
| Color: | Grey | Grey | Grey | Grey/Yellow | Grey |
| Texture: | Crmby/Fbrs | Crmby/Fbrs | Crmby/Fbrs | Crmby/Fbrs | Crmby/Fbrs |
| Description: | Material | Material | Material | Material | Material |
| Analysis: | PLM | PLM | PLM | PLM | PLM |
| Asbestiform Minerals | | | | | |
| % Chrysotile: | | | | | |
| % Amosite: | | | | | |
| % Crocidolite: | | | | | |
| % Tremolite - Actinolite: | | | | | |
| % Anthophyllite: | | | | | |
| % Total Asbestos: | ND | ND | ND | ND | ND |
| Other Materials | | | | | |
| % Cellulose: | | | | | |
| % Fiberglass: | >20 ≤ 30 | >20 ≤ 30 | >20 ≤ 30 | >30 ≤ 40 | >20 ≤ 30 |
| % Other Fibers: | >5 ≤ 10 | >5 ≤ 10 | >5 ≤ 10 | | >5 ≤ 10 |
| % Resin/Binder: | | | | | |
| % Non Fibrous: | >50 ≤ 60 | >50 ≤ 60 | >50 ≤ 60 | >50 ≤ 60 | >50 ≤ 60 |

ND = None Detected Trace = <1%

Special Prep Procedures: None.

*Notes: P. O. #: Not Available.


 Shawn Smythe
 Microscopist

All values are in area percent by visual estimate. The Federal Register Vol. 55 No. 224 Tuesday Nov. 20 1990 Rules and Regulations states "... If the asbestos content is estimated to be less than 10% by a method other than point counting, ... (the analysis) be repeated using the point counting technique by PLM." Any of the above samples can be reanalyzed by point counting at the client's request. Wherever possible, separate phases are analyzed and reported individually.

12/21/07

DataChem Laboratories
Polarized Light Microscopy
Asbestos Analytical Report

Client: Washington Closure Hanford

Location: 309

Set ID: 07-A-6729

| Client Sample ID: | J162V8 | J162K8 | J162K9 | J162L0 | J162L1 |
|--------------------------------|-------------|-------------|-------------|-------------|------------|
| DCL Sample ID: | 07-39418 | 07-39419 | 07-39420 | 07-39421 | 07-39422 |
| Macroscopic Examination | | | | | |
| Accepted/Rejected: | Accepted | Accepted | Accepted | Accepted | Accepted |
| Homogeneity: | Layered | Layered | Layered | Layered | Homog. |
| | Inseparable | Inseparable | Inseparable | Inseparable | |
| Color: | Yellow/Grey | Grey/Yellow | Grey/Yellow | Grey/Yellow | Grey |
| Texture: | Fbrs/Crmby | Crmby/Fbrs | Crmby/Fbrs | Crmby/Fbrs | Crmby/Fbrs |
| Description: | Material | Material | Material | Material | Material |
| Analysis: | PLM | PLM | PLM | PLM | PLM |

Asbestiform Minerals

% Chrysotile:

% Amosite:

% Crocidolite:

% Tremolite - Actinolite:

% Anthophyllite:

% Total Asbestos:

ND

ND

ND

ND

ND

Other Materials

% Cellulose:

% Fiberglass:

% Other Fibers:

>50 ≤ 60

>20 ≤ 30

>30 ≤ 40

>20 ≤ 30

>20 ≤ 30

>5 ≤ 10

>5 ≤ 10

>5 ≤ 10

% Resin/Binder:

% Non Fibrous:

>30 ≤ 40

>50 ≤ 60

>50 ≤ 60

>50 ≤ 60

>50 ≤ 60

ND = None Detected Trace = <1%

Special Prep Procedures: None.

*Notes: P. O. #: Not Available.


 Shawn Smythe
 Microscopist

All values are in area percent by visual estimate. The Federal Register Vol. 55 No. 224 Tuesday Nov. 20 1990 Rules and Regulations states "... If the asbestos content is estimated to be less than 10% by a method other than point counting,... (the analysis) be repeated using the point counting technique by PLM." Any of the above samples can be reanalyzed by point counting at the client's request. Wherever possible, separate phases are analyzed and reported individually.

12/21/07

DataChem Laboratories
Polarized Light Microscopy
Asbestos Analytical Report

Client: Washington Closure Hanford
 Location: 309
 Set ID: 07-A-6729

| Client Sample ID: | J162L2 | J162L3 | J162L4 | J162L5 | J162L6 |
|--------------------------------|--------------------|--------------------|--------------------|--------------------|--------------------|
| DCL Sample ID: | 07-39423 | 07-39424 | 07-39425 | 07-39426 | 07-39427 |
| Macroscopic Examination | | | | | |
| Accepted/Rejected: | Accepted | Accepted | Accepted | Accepted | Accepted |
| Homogeneity: | Homog. | Homog. | Homog. | Homog. | Homog. |
| Color: | Grey | Grey | Grey | Grey | Grey |
| Texture: | Crmby/Fbrs | Crmby/Fbrs | Crmby/Fbrs | Crmby/Fbrs | Crmby/Fbrs |
| Description: | Material | Material | Material | Material | Material |
| Analysis: | PLM | PLM | PLM | PLM | PLM |
| Asbestiform Minerals | | | | | |
| % Chrysotile: | | | | | |
| % Amosite: | | | | | |
| % Crocidolite: | | | | | |
| % Tremolite - Actinolite: | | | | | |
| % Anthophyllite: | | | | | |
| % Total Asbestos: | ND | ND | ND | ND | ND |
| Other Materials | | | | | |
| % Cellulose: | | | | | |
| % Fiberglass: | >20 ≤ 30 | >20 ≤ 30 | >30 ≤ 40 | >30 ≤ 40 | >20 ≤ 30 |
| % Other Fibers: | >5 ≤ 10 | >5 ≤ 10 | | | >5 ≤ 10 |
| % Resin/Binder: | | | | | |
| % Non Fibrous: | >50 ≤ 60 |

ND = None Detected Trace = <1%

Special Prep Procedures: None.

*Notes: P. O. #: Not Available.


 Shawn Smythe
 Microscopist

All values are in area percent by visual estimate. The Federal Register Vol. 55 No. 224 Tuesday Nov. 20 1990 Rules and Regulations states "... If the asbestos content is estimated to be less than 10% by a method other than point counting,... (the analysis) be repeated using the point counting technique by PLM." Any of the above samples can be reanalyzed by point counting at the client's request. Wherever possible, separate phases are analyzed and reported individually.

12/21/07

DataChem Laboratories
Polarized Light Microscopy
Asbestos Analytical Report

Client: Washington Closure Hanford
 Location: 309
 Set ID: 07-A-6729

| Client Sample ID: | J162L7 | J162L8 | J162L9 | J162M0 | J162M1 |
|--------------------------------|------------|------------|-------------|------------|------------|
| DCL Sample ID: | 07-39428 | 07-39429 | 07-39430 | 07-39431 | 07-39432 |
| Macroscopic Examination | | | | | |
| Accepted/Rejected: | Accepted | Accepted | Accepted | Accepted | Accepted |
| Homogeneity: | Homog. | Homog. | Homog. | Homog. | Homog. |
| Color: | Grey | Grey | Grey/Yellow | Grey | Grey |
| Texture: | Crmby/Fbrs | Crmby/Fbrs | Crmby/Fbrs | Crmby/Fbrs | Crmby/Fbrs |
| Description: | Material | Material | Material | Material | Material |
| Analysis: | PLM | PLM | PLM | PLM | PLM |
| Asbestiform Minerals | | | | | |
| % Chrysotile: | | | | | |
| % Amosite: | | | | | |
| % Crocidolite: | | | | | |
| % Tremolite - Actinolite: | | | | | |
| % Anthophyllite: | | | | | |
| % Total Asbestos: | ND | ND | ND | ND | ND |
| Other Materials | | | | | |
| % Cellulose: | | | | | |
| % Fiberglass: | >20 ≤ 30 | >20 ≤ 30 | >20 ≤ 30 | >20 ≤ 30 | >20 ≤ 30 |
| % Other Fibers: | >5 ≤ 10 | >5 ≤ 10 | >5 ≤ 10 | >5 ≤ 10 | >5 ≤ 10 |
| % Resin/Binder: | | | | | |
| % Non Fibrous: | >50 ≤ 60 | >50 ≤ 60 | >50 ≤ 60 | >50 ≤ 60 | >50 ≤ 60 |

ND = None Detected Trace = <1%

Special Prep Procedures: None.

*Notes: P. O. #: Not Available.


 Shawn Smythe
 Microscopist

All values are in area percent by visual estimate. The Federal Register Vol. 55 No. 224 Tuesday Nov. 20 1990 Rules and Regulations states "... If the asbestos content is estimated to be less than 10% by a method other than point counting,... (the analysis) be repeated using the point counting technique by PLM." Any of the above samples can be reanalyzed by point counting at the client's request. Wherever possible, separate phases are analyzed and reported individually.

12/21/07

**DataChem Laboratories
Polarized Light Microscopy
Asbestos Analytical Report**

Client: Washington Closure Hanford
Location: 309
Set ID: 07-A-6729

| Client Sample ID: | J162M2 | J162M3 | J162M4 | J162M9 | J162N0 |
|--------------------------------|------------|------------|------------|------------|------------|
| DCL Sample ID: | 07-39433 | 07-39434 | 07-39435 | 07-39440 | 07-39441 |
| Macroscopic Examination | | | | | |
| Accepted/Rejected: | Accepted | Accepted | Accepted | Accepted | Accepted |
| Homogeneity: | Homog. | Homog. | Homog. | Homog. | Homog. |
| Color: | Grey | Grey | Grey | Grey | Grey |
| Texture: | Crmby/Fbrs | Crmby/Fbrs | Crmby/Fbrs | Crmby/Fbrs | Crmby/Fbrs |
| Description: | Material | Material | Material | Material | Material |
| Analysis: | PLM | PLM | PLM | PLM | PLM |
| Asbestiform Minerals | | | | | |
| % Chrysotile: | | | | | |
| % Amosite: | | | | | |
| % Crocidolite: | | | | | |
| % Tremolite - Actinolite: | | | | | |
| % Anthophyllite: | | | | | |
| % Total Asbestos: | ND | ND | ND | ND | ND |
| Other Materials | | | | | |
| % Cellulose: | | | | | |
| % Fiberglass: | >20 ≤ 30 | >20 ≤ 30 | >20 ≤ 30 | >20 ≤ 30 | >20 ≤ 30 |
| % Other Fibers: | >5 ≤ 10 | >5 ≤ 10 | >5 ≤ 10 | >5 ≤ 10 | >5 ≤ 10 |
| % Resin/Binder: | | | | | |
| % Non Fibrous: | >50 ≤ 60 | >50 ≤ 60 | >50 ≤ 60 | >50 ≤ 60 | >50 ≤ 60 |

ND = None Detected Trace = <1%

Special Prep Procedures: Sample numbers J162M5 through J162M8 were prepared by gravimetric reduction.

*Notes: P. O. #: Not Available.


Shawn Smythe
Microscopist

All values are in area percent by visual estimate. The Federal Register Vol. 55 No. 224 Tuesday Nov. 20 1990 Rules and Regulations states "... If the asbestos content is estimated to be less than 10% by a method other than point counting,... (the analysis) be repeated using the point counting technique by PLM." Any of the above samples can be reanalyzed by point counting at the client's request. Wherever possible, separate phases are analyzed and reported individually.

12/21/07

**DataChem Laboratories
Polarized Light Microscopy
Asbestos Analytical Report**

Client: Washington Closure Hanford
Location: 309
Set ID: 07-A-6729

| Client Sample ID: | J162N1 | J162N2 | J162N3 | J162N4 | J162N5 |
|--------------------------------|------------|-------------|------------|------------|------------|
| DCL Sample ID: | 07-39442 | 07-39443 | 07-39444 | 07-39445 | 07-39446 |
| Macroscopic Examination | | | | | |
| Accepted/Rejected: | Accepted | Accepted | Accepted | Accepted | Accepted |
| Homogeneity: | Homog. | Homog. | Homog. | Homog. | Homog. |
| Color: | Grey | Grey/Yellow | Grey | Grey | Grey |
| Texture: | Crmby/Fbrs | Crmby/Fbrs | Crmby/Fbrs | Crmby/Fbrs | Crmby/Fbrs |
| Description: | Material | Material | Material | Material | Material |
| Analysis: | PLM | PLM | PLM | PLM | PLM |
| Asbestiform Minerals | | | | | |
| % Chrysotile: | | | | | |
| % Amosite: | | | | | |
| % Crocidolite: | | | | | |
| % Tremolite - Actinolite: | | | | | |
| % Anthophyllite: | | | | | |
| % Total Asbestos: | ND | ND | ND | ND | ND |
| Other Materials | | | | | |
| % Cellulose: | | | | | |
| % Fiberglass: | >20 ≤ 30 | >20 ≤ 30 | >20 ≤ 30 | >20 ≤ 30 | >20 ≤ 30 |
| % Other Fibers: | >5 ≤ 10 | >5 ≤ 10 | >5 ≤ 10 | >5 ≤ 10 | >5 ≤ 10 |
| % Resin/Binder: | | | | | |
| % Non Fibrous: | >50 ≤ 60 | >50 ≤ 60 | >50 ≤ 60 | >50 ≤ 60 | >50 ≤ 60 |

ND = None Detected Trace = <1%

Special Prep Procedures: None.

*Notes: P. O. #: Not Available.


Shawn Smythe
Microscopist

All values are in area percent by visual estimate. The Federal Register Vol. 55 No. 224 Tuesday Nov. 20 1990 Rules and Regulations states "... If the asbestos content is estimated to be less than 10% by a method other than point counting,... (the analysis) be repeated using the point counting technique by PLM." Any of the above samples can be reanalyzed by point counting at the client's request. Wherever possible, separate phases are analyzed and reported individually.

12/21/07

**DataChem Laboratories
Polarized Light Microscopy
Asbestos Analytical Report**

Client: Washington Closure Hanford
Location: 309
Set ID: 07-A-6729

| Client Sample ID: | J162N6 | J162N7 | J162N8 |
|-------------------|----------|----------|----------|
| DCL Sample ID: | 07-39447 | 07-39448 | 07-39449 |

Macroscopic Examination

| | | | |
|--------------------|------------|------------|------------|
| Accepted/Rejected: | Accepted | Accepted | Accepted |
| Homogeneity: | Homog. | Homog. | Homog. |
| Color: | Grey | Grey | Grey |
| Texture: | Crmby/Fbrs | Crmby/Fbrs | Crmby/Fbrs |
| Description: | Material | Material | Material |
| Analysis: | PLM | PLM | PLM |

Asbestiform Minerals

| | | | |
|---------------------------|-----------|-----------|-----------|
| % Chrysotile: | | | |
| % Amosite: | | | |
| % Crocidolite: | | | |
| % Tremolite - Actinolite: | | | |
| % Anthophyllite: | | | |
| % Total Asbestos: | ND | ND | ND |

Other Materials

| | | | |
|-----------------|----------|----------|----------|
| % Cellulose: | | | |
| % Fiberglass: | >20 ≤ 30 | >20 ≤ 30 | >20 ≤ 30 |
| % Other Fibers: | >5 ≤ 10 | >5 ≤ 10 | >5 ≤ 10 |
| % Resin/Binder: | | | |
| % Non Fibrous: | >50 ≤ 60 | >50 ≤ 60 | >50 ≤ 60 |

ND = None Detected Trace = <1%

Special Prep Procedures: Sample numbers J162N9 through J162V9 were prepared by gravimetric reduction.

*Notes: P. O. #: Not Available.


Shawn Smythe
Microscopist

All values are in area percent by visual estimate. The Federal Register Vol. 55 No. 224 Tuesday Nov. 20 1990 Rules and Regulations states "... If the asbestos content is estimated to be less than .10% by a method other than point counting,... (the analysis) be repeated using the point counting technique by PLM." Any of the above samples can be reanalyzed by point counting at the client's request. Wherever possible, separate phases are analyzed and reported individually.



SUBMITTED TO:

Joan Kessner
Washington Closure Hanford
2620 Fermi Avenue, MSIN H4-21
Richland, WA 99354


REFERENCE DATA:

| | |
|----------------------|---|
| Client Sample No.: | J162M5 through J162V9 |
| P.O. No.: | Not Available |
| Sample Location: | 309 |
| Sample Type: | Bulk |
| Method Reference: | EPA/600/R-93/116, ELAP 198.1 (modified), PLM Analysis with Gravimetric Reduction |
| DCL Set ID No.: | 07-A-6729 |
| DCL Sample ID No.: | 07-39436 through 07-39452 |
| Sample Receipt Date: | 11/27/07 |
| Preparation Date: | 12/19/07 through 12/20/07 |
| Analysis Date: | 12/20/07 |

We certify that the samples indicated on the following data sheet(s) were prepared by gravimetric reduction and analyzed by Polarized Light Microscopy (PLM) for asbestos using a modification of the method, EPA/600/R-93/116, ELAP 198.1, Chatfield Method, for determining the amount and type of asbestos present in bulk building materials. The samples were acceptable upon receipt except where noted.

The samples were examined under a stereomicroscope for general composition and phase separation. Coarse, non-asbestos materials that cannot be pulverized, such as pebbles or metal foils, were separated from the portion analyzed. Other non-asbestos material was removed by ashing in a muffle furnace and/or dissolution in hydrochloric acid. Sample weights were tracked through each step in the reduction. Mountings of representative portions of the final residue were prepared in one or more refractive index liquids (1.550, 1.605, 1.680) and examined by Polarized Light Microscopy*. Estimates of concentration are made on an area basis. The results of the analysis apply only to the materials analyzed and are summarized on the attached PLM Asbestos Analysis Data Sheets.


Shawn Smythe
Analyst


for Anna Marie Ristich
Reviewer

* Some samples may contain fibers that are not visible by PLM and can only be discovered by electron microscopy techniques. Floor tiles are analyzed as homogeneous materials if insufficient mastic is present or if phases have been cross contaminated.

DataChem Laboratories NVLAP Lab ID: 101917. Laboratory accreditation by the National Institute of Standards and Technology does not in any way constitute approval or endorsement by NVLAP, NIST, or any agency of the federal government.

Samples will be disposed of after 60 days unless instructed otherwise.

CINCINNATI OFFICE
4388 GLENDALE-MILFORD ROAD
CINCINNATI, OHIO 45242-3706
513 733-5336, FAX 513 733-5347

WEST COAST OFFICE
11 SANTA YORMA COURT
NOVATO, CALIFORNIA 94945
800 280-8071, FAX 415 883-9469

DataChem Laboratories Analytical Report
PLM Bulk Asbestos Analysis using Gravimetric Reduction

Client: Washington Closure Hanford
Location: 309
Set ID: 07-A-6729


| SAMPLE IDENTIFICATION | | | | | |
|---|----------|----------|----------|----------|----------|
| Client ID: | J162M5 | J162M6 | J162M7 | J162M8 | J162N9 |
| DCL ID: | 07-39436 | 07-39437 | 07-39438 | 07-39439 | 07-39450 |
| SAMPLE DESCRIPTION | | | | | |
| Homogeneity: | Homog. | Homog. | Homog. | Homog. | Homog. |
| Color: | Black | Black | Black | Black | Black |
| Texture: | Resinous | Resinous | Resinous | Resinous | Resinous |
| Description: | Roofing | Roofing | Roofing | Roofing | Roofing |
| SAMPLE PREP | | | | | |
| Starting Weight (g): | 0.2511 | 0.3245 | 0.3890 | 0.2998 | 0.1614 |
| Residue Weight (g): | 0.0039 | 0.0070 | 0.0340 | 0.0152 | 0.0071 |
| Weight Percent Residue: | 1.55 | 2.16 | 8.74 | 5.07 | 4.40 |
| PERCENT ASBESTOS DETECTED IN RESIDUE | | | | | |
| Chrysotile: | ND | ND | 30 | ND | ND |
| Grunerite: | ND | ND | 0 | ND | ND |
| Crocidolite: | ND | ND | 0 | ND | ND |
| Actinolite-Tremolite: | ND | ND | 0 | ND | ND |
| Anthophyllite: | ND | ND | 0 | ND | ND |
| TOTAL IN RESIDUE | ND | ND | 30.0 | ND | ND |
| ASBESTOS PERCENT IN SAMPLE | | | | | |
| | ND | ND | 2.6 | ND | ND |

ND = None Detected

TRACE = <1%

*Notes: P. O. #: Not Available.


Shawn Smythe
Analyst


Anna Marie Ristich
Reviewer

**DataChem Laboratories Analytical Report
PLM Bulk Asbestos Analysis using Gravimetric Reduction**

Client: Washington Closure Hanford
Location: 309
Set ID: 07-A-6729


| SAMPLE IDENTIFICATION | | |
|---|-------------|-----------|
| Client ID: | J162P0 | J162V9 |
| DCL ID: | 07-39451 | 07-39452 |
| SAMPLE DESCRIPTION | | |
| Homogeneity: | Homog. | Homog. |
| Color: | Black | Black |
| Texture: | Resinous | Resinous |
| Description: | Roofing | Roofing |
| SAMPLE PREP | | |
| Starting Weight (g): | 0.2035 | 0.3268 |
| Residue Weight (g): | 0.0179 | 0.0022 |
| Weight Percent Residue: | 8.80 | 0.67 |
| PERCENT ASBESTOS DETECTED IN RESIDUE | | |
| Chrysotile: | 30 | ND |
| Grunerite: | 0 | ND |
| Crocidolite: | 0 | ND |
| Actinolite-Tremolite: | 0 | ND |
| Anthophyllite: | 0 | ND |
| TOTAL IN RESIDUE | 30.0 | ND |
| ASBESTOS PERCENT IN SAMPLE | | |
| | 2.6 | ND |

ND = None Detected

TRACE = <1%

*Notes: P. O. #: Not Available.


Shawn Smythe
Analyst


for Anna Marie Ristich
Reviewer

| Washington Closure Hanford | | CHAIN OF CUSTODY/SAMPLE ANALYSIS REQUEST | | | | RC-040-340 | | Page 1 of 10 | |
|--|-------------|--|-------------|---------------------------|--|---|--|---|--|
| Collector Mike Stankovich | | Company Contact MT Stankovich | | Telephone No. 531-7620 | | Project Coordinator KESSNER, JH | | Price Code 9K | |
| Project Designation 300 Area D&D Waste Characterization Sampling - Other Soli | | Sampling Location 309 | | SAF No. RC-040 | | Data Turnaround 7 Days | | | |
| Ice Chest No. Fed Ex Box | | Field Logbook No. EL-1518-9 | | COA See below | | Method of Shipment Federal Express | | | |
| Shipped To DataChem Laboratories - Cincinnati | | Offsite Property No. A080037 | | | | Bill of Lading/Air Bill No. See OSPC | | | |
| POSSIBLE SAMPLE HAZARDS/REMARKS Asbestos & Be | | Preservation | | None | | | | | |
| Special Handling and/or Storage | | Type of Container | | G/P | | | | | |
| | | No. of Container(s) | | 1 | | | | | |
| | | Volume | | 5g | | | | | |
| SAMPLE ANALYSIS | | | | Asbestos-BULK-EPA | | | | | |
| 07-A6729 | | | | | | | | | |
| Sample No. | Matrix * | Sample Date | Sample Time | | | | | | |
| J162V3 39413 | OTHER SOLID | 11-26-07 | 0939 | | | | | | |
| J162V4 39414 | OTHER SOLID | | 0942 | | | | | | |
| J162V5 39415 | OTHER SOLID | | 0945 | | | | | | |
| J162V6 39416 | OTHER SOLID | | 0948 | | | | | | |
| J162V7 39417 | OTHER SOLID | | 0951 | | | | | | |
| CHAIN OF POSSESSION | | Sign/Print Names | | | | SPECIAL INSTRUCTIONS | | | |
| Relinquished By/Removed From | | Date/Time | | Received By/Stored In | | Date/Time | | Laboratory Analysis, Data Management, and Shipping COA - RD4MXX2F00 | |
| M. Stankovich | | 11/26/07 1030 | | M. Stankovich | | 11-26-07 1030 | | | |
| Relinquished By/Removed From | | Date/Time | | Received By/Stored In | | Date/Time | | | |
| Bill Stankovich | | 11-26-07 1500 | | FED. EX | | | | | |
| Relinquished By/Removed From | | Date/Time | | Received By/Stored In | | Date/Time | | | |
| | | | | | | 11/27/07 | | | |
| Relinquished By/Removed From | | Date/Time | | Received By/Stored In | | Date/Time | | | |
| | | | | | | | | | |
| Relinquished By/Removed From | | Date/Time | | Received By/Stored In | | Date/Time | | | |
| | | | | | | | | | |
| LABORATORY SECTION | | Received By | | Title | | Date/Time | | | |
| FINAL SAMPLE DISPOSITION | | Disposal Method | | Disposed By | | Date/Time | | | |

| Washington Closure Hanford | | CHAIN OF CUSTODY/SAMPLE ANALYSIS REQUEST | | | | RC-040-339 | | Page 4 of 10 | |
|--|-----------------|--|-----------------------|---|------------------|--|--|---|--|
| Collector Mike Stankovich | | Company Contact MT Stankovich | | Telephone No. 531-7620 | | Project Coordinator KESSNER, JH | | Price Code 9K Data Turnaround 7 Days | |
| Project Designation 300 Area D&D Waste Characterization Sampling - Other Soli | | Sampling Location 309 | | SAF No. RC-040 | | | | | |
| Ice Chest No. Fed Ex Box | | Field Logbook No. EL-1518-9 | | COA Sec below | | Method of Shipment Federal Express | | | |
| Shipped To DataChem Laboratories - Cincinnati | | Offsite Property No. A080037 | | Bill of Lading/Air Bill No. Sec OSPC | | | | | |
| POSSIBLE SAMPLE HAZARDS/REMARKS <i>Asbestos & Be</i> | | | | Preservation | None | | | | |
| Special Handling and/or Storage | | | | Type of Container | G/P | | | | |
| | | | | No. of Container(s) | 1 | | | | |
| | | | | Volume | 5g | | | | |
| SAMPLE ANALYSIS 6729 | | | | Asbestos-BULK-EPA | | | | | |
| Sample No. | Matrix * | Sample Date | Sample Time | | | | | | |
| J162K7 <i>39418</i> | OTHER SOLID | 11-26-07 | 0959 | X | | | | | |
| J162K8 <i>39419</i> | OTHER SOLID | 11-26-07 | 0800 | X | | | | | |
| J162K9 <i>39420</i> | OTHER SOLID | | 0803 | X | | | | | |
| J162L0 <i>39421</i> | OTHER SOLID | | 0806 | X | | | | | |
| J162L1 <i>39422</i> | OTHER SOLID | | 0809 | X | | | | | |
| CHAIN OF POSSESSION | | | Sign/Print Names | | | SPECIAL INSTRUCTIONS | | | |
| Relinquished By/Removed From | | Date/Time | Received By/Stored In | | Date/Time | Laboratory Analysis, Data Management, and Shipping COA - RD4MXX2F00 | | | |
| <i>MT Stankovich</i> | | 1030 11-26-07 | <i>MT Stankovich</i> | | 1030 11-26-07 | | | | |
| Relinquished By/Removed From | | Date/Time | Received By/Stored In | | Date/Time | | | | |
| <i>MT Stankovich</i> | | 4011 11-26-07 1500 | <i>FED EX</i> | | | | | | |
| Relinquished By/Removed From | | Date/Time | Received By/Stored In | | Date/Time | | | | |
| | | | <i>[Signature]</i> | | 11/27/07 | | | | |
| Relinquished By/Removed From | | Date/Time | Received By/Stored In | | Date/Time | Matrix * S=Soil SE=Sediment SO=Solid Sl=Sludge W=Water O=Oil A=Air DS=Drum Solids DL=Drum Liquids T=Tissue Wf=Wipe L=Liquid V=Vegetation X=Other | | | |
| Relinquished By/Removed From | | Date/Time | Received By/Stored In | | Date/Time | | | | |
| Relinquished By/Removed From | | Date/Time | Received By/Stored In | | Date/Time | | | | |
| Relinquished By/Removed From | | Date/Time | Received By/Stored In | | Date/Time | | | | |
| LABORATORY SECTION | Received By | | Title | | | Date/Time | | | |
| FINAL SAMPLE DISPOSITION | Disposal Method | | Disposed By | | | Date/Time | | | |

| Washington Closure Hanford | | CHAIN OF CUSTODY/SAMPLE ANALYSIS REQUEST | | | | RC-040-339 | | Page 2 of 10 | | | | | | | | | | | | | |
|--|-------------|--|-----------------------|---------------------------|---------------------|---|-----------|--|----------------------|--|--|--|----------|--|--|--|--|--|--|--|--|
| Collector Mike Stankovich | | Company Contact MT Stankovich | | Telephone No. 531-7620 | | Project Coordinator KESSNER, JH | | Price Code 9K Data Turnaround 7 Days | | | | | | | | | | | | | |
| Project Designation 300 Area D&D Waste Characterization Sampling - Other Soli | | Sampling Location 309 | | SAF No. RC-040 | | | | | | | | | | | | | | | | | |
| Ice Chest No. Fed Ex Box | | Field Logbook No. EL-1518-9 | | COA See below | | Method of Shipment Federal Express | | | | | | | | | | | | | | | |
| Shipped To DataChem Laboratories - Cincinnati | | Offsite Property No. A080037 | | | | Bill of Lading/Air Bill No. See OSPC | | | | | | | | | | | | | | | |
| POSSIBLE SAMPLE HAZARDS/REMARKS Asbestos & Be | | | | | Preservation | None | | | | | | | | | | | | | | | |
| Special Handling and/or Storage | | | | | Type of Container | G/P | | | | | | | | | | | | | | | |
| | | | | | No. of Container(s) | 1 | | | | | | | | | | | | | | | |
| | | | | | Volume | 5g | | | | | | | | | | | | | | | |
| SAMPLE ANALYSIS | | | | | Asbestos-BULK-EPA | | | | | | | | | | | | | | | | |
| | | | | | 6729 | | | | | | | | | | | | | | | | |
| Sample No. | Matrix * | Sample Date | Sample Time | | | | | | | | | | | | | | | | | | |
| J162L2 39423 | OTHER SOLID | 11-26-07 | 0812 | X | | | | | | | | | | | | | | | | | |
| J162L3 39424 | OTHER SOLID | ↓ | 0815 | T | | | | | | | | | | | | | | | | | |
| J162L4 39425 | OTHER SOLID | | 0818 | T | | | | | | | | | | | | | | | | | |
| J162L5 39426 | OTHER SOLID | | 0821 | X | | | | | | | | | | | | | | | | | |
| J162L6 39427 | OTHER SOLID | | 0824 | X | | | | | | | | | | | | | | | | | |
| CHAIN OF POSSESSION | | | | | Sign/Print Names | | | | SPECIAL INSTRUCTIONS | | | | Matrix * | | | | | | | | |
| Relinquished By/Removed From | | Date/Time | Received By/Stored In | | Date/Time | Laboratory Analysis, Data Management, and Shipping COA - RD4MXX2F00 | | | | S=Soil SE=Settlement SO=Solid SL=Sludge W=Water O=Oil A=Air DS=Drum Solids DL=Drum Liquids T=Tissue WI=Wipe L=Liquid V=Vegetation X=Other | | | | | | | | | | | |
| MT Stankovich | | 11/26/07 1030 | MT Stankovich | | 11-26-07 1030 | | | | | | | | | | | | | | | | |
| Relinquished By/Removed From | | Date/Time | Received By/Stored In | | Date/Time | | | | | | | | | | | | | | | | |
| MT Stankovich | | 11-26-07 1500 | FED EX | | | | | | | | | | | | | | | | | | |
| Relinquished By/Removed From | | Date/Time | Received By/Stored In | | Date/Time | | | | | | | | | | | | | | | | |
| | | | JH | | 11/27/07 | | | | | | | | | | | | | | | | |
| Relinquished By/Removed From | | Date/Time | Received By/Stored In | | Date/Time | | | | | | | | | | | | | | | | |
| | | | | | | | | | | | | | | | | | | | | | |
| Relinquished By/Removed From | | Date/Time | Received By/Stored In | | Date/Time | | | | | | | | | | | | | | | | |
| | | | | | | | | | | | | | | | | | | | | | |
| LABORATORY SECTION | | Received By | Title | | | | Date/Time | | | | | | | | | | | | | | |
| FINAL SAMPLE DISPOSITION | | Disposal Method | Disposed By | | | | Date/Time | | | | | | | | | | | | | | |

| Washington Closure Hanford | | CHAIN OF CUSTODY/SAMPLE ANALYSIS REQUEST | | | | RC-040-339 | Page 6 of 10 | |
|--|-------------|--|-------------|---|------|---------------------------------------|---------------|---|
| Collector Mike Stankovich | | Company Contact MT Stankovich | | Telephone No. 531-7620 | | Project Coordinator KESSNER, JH | Price Code 9K | Data Turnaround 7 Days |
| Project Designation 300 Area D&D Waste Characterization Sampling - Other Soli | | Sampling Location 309 | | SAF No. RC-040 | | | | |
| Ice Chest No. Fed Ex Box | | Field Logbook No. EL-1518-9 | | COA See below | | Method of Shipment Federal Express | | |
| Shipped To DataChem Laboratories - Cincinnati | | Offsite Property No. A080037 | | Bill of Lading/Air Bill No. See OSPC | | | | |
| POSSIBLE SAMPLE HAZARDS/REMARKS Asbestos & Be | | | | Preservation | None | | | |
| Special Handling and/or Storage | | | | Type of Container | GP | | | |
| | | | | No. of Container(s) | 1 | | | |
| | | | | Volume | 5g | | | |
| SAMPLE ANALYSIS 6729 | | | | Asbestos-BULK-EPA | | | | |
| Sample No. | Matrix * | Sample Date | Sample Time | | | | | |
| J162L7 39428 | OTHER SOLID | 11-26-07 | 0827 | X | | | | |
| J162L8 39429 | OTHER SOLID | ↓ | 0830 | X | | | | |
| J162L9 39430 | OTHER SOLID | | 0833 | X | | | | |
| J162M0 39431 | OTHER SOLID | | 0836 | X | | | | |
| J162M1 39402 | OTHER SOLID | | 0839 | X | | | | |
| CHAIN OF POSSESSION | | | | SPECIAL INSTRUCTIONS | | | | Matrix * |
| Relinquished By/Removed From | | Date/Time | | Received By/Stored In | | Date/Time | | Laboratory Analysis, Data Management, and Shipping COA - RD4MXX2F00 S=Soil SE=Softmet SO=Solid SL=Sludge W=Water O=Oil A=Air DS=Dryn Solids DL=Dryn L Liquids T=Tissue W=Wipe L=Liquid V=Vegetation X=Other |
| M. Stankovich mstankovich | | 11/26/07 1030 | | M. Stankovich M Stankovich | | 11-26-07 1030 | | |
| M. Stankovich M Stankovich | | 11-26-07 1500 | | KERRIN | | | | |
| | | | | M. Stankovich M Stankovich | | 11/27/07 | | |
| Relinquished By/Removed From | | Date/Time | | Received By/Stored In | | Date/Time | | |
| Relinquished By/Removed From | | Date/Time | | Received By/Stored In | | Date/Time | | |
| Relinquished By/Removed From | | Date/Time | | Received By/Stored In | | Date/Time | | |
| LABORATORY SECTION | | Received By | | Title | | Date/Time | | |
| FINAL SAMPLE DISPOSITION | | Disposal Method | | Disposed By | | Date/Time | | |

| Washington Closure Hanford | | CHAIN OF CUSTODY/SAMPLE ANALYSIS REQUEST | | | | RC-040-339 | | Page 1 of 10 | | | | | | | | | |
|---|-------------|--|-------------|---|------|---------------------------------------|--|---|--|--|--|--|--|--|--|--|--|
| Collector Mike Stankovich | | Company Contact MT Stankovich | | Telephone No. 531-7620 | | Project Coordinator KESSNER, JH | | Price Code 9K Data Turnaround 7 Days | | | | | | | | | |
| Project Designation 300 Area D&D Waste Characterization Sampling - Other Soli | | Sampling Location 309 | | SAF No. RC-040 | | | | | | | | | | | | | |
| Ice Chest No. Fed Ex Box | | Field Logbook No. EL-1518-9 | | COA See below | | Method of Shipment Federal Express | | | | | | | | | | | |
| Shipped To DataChem Laboratories - Cincinnati | | Offsite Property No. A080037 | | Bill of Lading/Air Bill No. See OSPC | | | | | | | | | | | | | |
| POSSIBLE SAMPLE HAZARDS/REMARKS Asbestos & Be Special Handling and/or Storage | | | | Preservation | None | | | | | | | | | | | | |
| | | | | Type of Container | G/P | | | | | | | | | | | | |
| | | | | No. of Container(s) | 1 | | | | | | | | | | | | |
| | | | | Volume | 5g | | | | | | | | | | | | |
| SAMPLE ANALYSIS 6728 | | | | Asbestos-BULK-EPA | | | | | | | | | | | | | |
| | | | | | | | | | | | | | | | | | |
| Sample No. | Matrix * | Sample Date | Sample Time | | | | | | | | | | | | | | |
| J162M2 39433 | OTHER SOLID | 11-26-07 | 0842 | X | | | | | | | | | | | | | |
| J162M3 39434 | OTHER SOLID | ↓ | 0845 | X | | | | | | | | | | | | | |
| J162M4 39435 | OTHER SOLID | | 0848 | X | | | | | | | | | | | | | |
| J162M5 39436 | OTHER SOLID | | 0851 | X | | | | | | | | | | | | | |
| J162M6 39437 | OTHER SOLID | | 0854 | X | | | | | | | | | | | | | |
| CHAIN OF POSSESSION | | | | Sign/Print Names | | | | SPECIAL INSTRUCTIONS | | | | Matrix * | | | | | |
| Relinquished By/Removed From | | Date/Time 1630 | | Received By/Stored In | | Date/Time | | Laboratory Analysis, Data Management, and Shipping COA - RD4MXX2F00 | | | | <ul style="list-style-type: none"> S=Soil SE=Sediment SO=Solid SL=Sludge W=Water O=Oil A=Air DS=Drum Solids DL=Drum Liquids T=Times W/W=Pipe L=Liquid V=Vegetation X=Other | | | | | |
| M.L. STANKOVICH | | 11/24/07 | | M. Stankovich | | 11-26-07 1030 | | | | | | | | | | | |
| M.L. STANKOVICH | | 11-26-07 1300 | | FED EX | | | | | | | | | | | | | |
| | | | | J. [Signature] | | 11/27/07 | | | | | | | | | | | |
| | | | | | | | | | | | | | | | | | |
| | | | | | | | | | | | | | | | | | |
| LABORATORY SECTION | | Received By | | Title | | Date/Time | | | | | | | | | | | |
| FINAL SAMPLE DISPOSITION | | Disposal Method | | Disposed By | | | | Date/Time | | | | | | | | | |

| Washington Closure Hanford | | CHAIN OF CUSTODY/SAMPLE ANALYSIS REQUEST | | | | RC-040-339 | Page 2 of 10 | |
|--|-------------------|--|------------------|---|------------------------------------|---------------|---------------------------|--|
| Collector Mike Stankovich | | Company Contact MT Stankovich | | Telephone No. 531-7620 | Project Coordinator KESSNER, JH | Price Code 9K | Data Turnaround 7 Days | |
| Project Designation 300 Area D&D Waste Characterization Sampling - Other Soli | | Sampling Location 309 | | SAF No. RC-040 | | | | |
| Ice Chest No. Fed Ex Box | | Field Logbook No. EL-1518-9 | COA See below | Method of Shipment Federal Express | | | | |
| Shipped To DataChem Laboratories - Cincinnati | | Offsite Property No. A080637 | | Bill of Lading/Air Bill No. See OSPC | | | | |
| POSSIBLE SAMPLE HAZARDS/REMARKS Asbestos & Be | | Preservation | None | | | | | |
| Special Handling and/or Storage | | Type of Container | G/P | | | | | |
| | | No. of Container(s) | 1 | | | | | |
| | | Volume | 5g | | | | | |
| SAMPLE ANALYSIS | | Asbestos-BULK-EPA | 6729 | | | | | |
| Sample No. | Matrix * | Sample Date | Sample Time | | | | | |
| J162M7 | 39438 OTHER SOLID | 11-26-07 | 0857 | X | | | | |
| J162M8 | 39439 OTHER SOLID | ↓ | 0900 | X | | | | |
| J162M9 | 39440 OTHER SOLID | ↓ | 0903 | X | | | | |
| J162N0 | 39441 OTHER SOLID | ↓ | 0906 | X | | | | |
| J162N1 | 39442 OTHER SOLID | ↓ | 0909 | X | | | | |
| CHAIN OF POSSESSION | | Sign/Print Names | | SPECIAL INSTRUCTIONS | | | | Matrix * |
| Relinquished By/Removed From | Date/Time | Received By/Stored In | Date/Time | Laboratory Analysis, Data Management, and Shipping COA - RD4MXX2F00 | | | | S=Soil SE=Sediment SO=Solid SL=Sludge W=Water O=Oil A=Air DS=Drum Solids DL=Drum Liquids T=Tissue Wl=Wipe L=Liquid V=Vegetation X=Other |
| MULL | 11/26/07 1030 | MT Stankovich | 11-26-07 1030 | | | | | |
| Relinquished By/Removed From | Date/Time | Received By/Stored In | Date/Time | | | | | |
| MT Stankovich | 11-26-07 1500 | FED EX | | | | | | |
| Relinquished By/Removed From | Date/Time | Received By/Stored In | Date/Time | | | | | |
| Relinquished By/Removed From | Date/Time | Received By/Stored In | Date/Time | | | | | |
| Relinquished By/Removed From | Date/Time | Received By/Stored In | Date/Time | | | | | |
| Relinquished By/Removed From | Date/Time | Received By/Stored In | Date/Time | | | | | |
| LABORATORY SECTION | Received By | Title | | | | | Date/Time | |
| FINAL SAMPLE DISPOSITION | Disposal Method | Disposed By | | | | | Date/Time | |

| Washington Closure Hanford | | CHAIN OF CUSTODY/SAMPLE ANALYSIS REQUEST | | | | RC-040-339 | | Page 2 of 10 | | | | | | | | | | | | |
|--|-------------------|--|-------------|---|------|---------------------------------------|--|---|--|--|--|--|--|--|--|--|--|--|--|--|
| Collector Mike Stankovich | | Company Contact MT Stankovich | | Telephone No. 531-7620 | | Project Coordinator KESSNER, JH | | Price Code 9K Data Turnaround 7 Days | | | | | | | | | | | | |
| Project Designation 300 Area D&D Waste Characterization Sampling - Other Soli | | Sampling Location 309 | | SAF No. RC-040 | | | | | | | | | | | | | | | | |
| Ice Chest No. Fed Ex Box | | Field Logbook No. EL-1518-9 | | COA See below | | Method of Shipment Federal Express | | | | | | | | | | | | | | |
| Shipped To DataChem Laboratories - Cincinnati | | Offsite Property No. A080037 | | Bill of Lading/Air Bill No. See OSCP | | | | | | | | | | | | | | | | |
| POSSIBLE SAMPLE HAZARDS/REMARKS <i>Asbestos & Be</i> | | | | Preservation | None | | | | | | | | | | | | | | | |
| Special Handling and/or Storage | | | | Type of Container | G/P | | | | | | | | | | | | | | | |
| | | | | No. of Container(s) | 1 | | | | | | | | | | | | | | | |
| | | | | Volume | 5g | | | | | | | | | | | | | | | |
| SAMPLE ANALYSIS 6729 | | | | Asbestos- BULK-EPA | | | | | | | | | | | | | | | | |
| Sample No. | Matrix * | Sample Date | Sample Time | | | | | | | | | | | | | | | | | |
| J162N2 | 39443 OTHER SOLID | 11-26-07 | 0912 | X | | | | | | | | | | | | | | | | |
| J162N3 | 39444 OTHER SOLID | ↓ | 0915 | T | | | | | | | | | | | | | | | | |
| J162N4 | 39445 OTHER SOLID | | 0918 | T | | | | | | | | | | | | | | | | |
| J162N5 | 39446 OTHER SOLID | | 0921 | T | | | | | | | | | | | | | | | | |
| J162N6 | 39447 OTHER SOLID | | 0924 | T | | | | | | | | | | | | | | | | |
| CHAIN OF POSSESSION | | | | Sign/Print Names | | | | SPECIAL INSTRUCTIONS | | | | Matrix * | | | | | | | | |
| Relinquished By/Removed From | | Date/Time | | Received By/Stored In | | Date/Time | | Laboratory Analysis, Data Management, and Shipping COA - RD4MXX2F00 | | | | S=Soil SB=Soilment SO=Solid SI=Sludge W=Water O=Oil A=Air DS=Drum Solids DL=Drum Liquids T=Tissue WJ=Wipe L=Liquid V=Vegetation X=Other | | | | | | | | |
| <i>M. Stankovich</i> | | 1030 11/26/07 | | <i>M. Stankovich</i> | | 11-26-07 1030 | | | | | | | | | | | | | | |
| <i>M. Stankovich</i> | | 1500 11-26-07 | | FEPEX | | | | | | | | | | | | | | | | |
| <i>[Signature]</i> | | | | <i>[Signature]</i> | | 11/27/07 | | | | | | | | | | | | | | |
| Relinquished By/Removed From | | Date/Time | | Received By/Stored In | | Date/Time | | | | | | | | | | | | | | |
| Relinquished By/Removed From | | Date/Time | | Received By/Stored In | | Date/Time | | | | | | | | | | | | | | |
| Relinquished By/Removed From | | Date/Time | | Received By/Stored In | | Date/Time | | | | | | | | | | | | | | |
| LABORATORY SECTION | | Received By | | Title | | | | Date/Time | | | | | | | | | | | | |
| FINAL SAMPLE DISPOSITION | | Disposal Method | | Disposed By | | | | Date/Time | | | | | | | | | | | | |

| | | | | | | | |
|--|-----------------|---|-----------------------|---|---|--|---------------|
| Washington Closure Hanford | | CHAIN OF CUSTODY/SAMPLE ANALYSIS REQUEST | | | | RC-040-339 | Page 10 of 10 |
| Collector Mike Stankovich | | Company Contact MT Stankovich | | Telephone No. 531-7620 | | Project Coordinator KESSNER, JH | |
| Project Designation 300 Area D&D Waste Characterization Sampling - Other Soli | | Sampling Location 309 | | SAF No. RC-040 | | Price Code 9K Data Turnaround 7 Days | |
| Ice Chest No. Fed Ex Box | | Field Logbook No. EL-1518-9 | | COA See below | | Method of Shipment Federal Express | |
| Shipped To DataChem Laboratories - Cincinnati | | Offsite Property No. A080037 | | Bill of Lading/Air Bill No. See OSPC | | | |
| POSSIBLE SAMPLE HAZARDS/REMARKS <i>Asbestos & Be</i> | | Preservation | | None | | | |
| Special Handling and/or Storage | | Type of Container | | G/P | | | |
| | | No. of Container(s) | | 1 | | | |
| | | Volume | | 5g | | | |
| SAMPLE ANALYSIS | | | | Asbestos- BULK-EPA | | | |
| | | 6729 | | | | | |
| Sample No. | Matrix * | Sample Date | Sample Time | | | | |
| J162N7 39448 | OTHER SOLID | 11-26-07 | 0927 | | | | |
| J162N8 39449 | OTHER SOLID | } | 0930 | | | | |
| J162N9 39450 | OTHER SOLID | | 0933 | | | | |
| J162P0 39451 | OTHER SOLID | | 0936 | | | | |
| J162U98452 | other solid | | 0957 | | | | |
| CHAIN OF POSSESSION | | | Sign/Print Names | | SPECIAL INSTRUCTIONS | | |
| Relinquished By/Removed From | | Date/Time | Received By/Stored In | | Laboratory Analysis, Data Management, and Shipping COA - RD4MXX2F00 | | |
| <i>M Stankovich</i> | | 11/24/07 1030 | <i>M Stankovich</i> | | 11-26-07 1030 | | |
| Relinquished By/Removed From | | Date/Time | Received By/Stored In | | Matrix * | | |
| <i>M Stankovich</i> | | 11-26-07 1500 | FED EX | | S=Soil SE=Soil/rock SO=Solid SL=Sludge W=Water O=Oil A=Air DS=Drum Solids DL=Drum Liquids T=Tissue Wl=Wipe L=Liquid V=Vegetation X=Other | | |
| Relinquished By/Removed From | | Date/Time | Received By/Stored In | | 11/27/07 | | |
| Relinquished By/Removed From | | Date/Time | Received By/Stored In | | | | |
| Relinquished By/Removed From | | Date/Time | Received By/Stored In | | | | |
| Relinquished By/Removed From | | Date/Time | Received By/Stored In | | | | |
| LABORATORY SECTION | Received By | Title | | Date/Time | | | |
| FINAL SAMPLE DISPOSITION | Disposal Method | Disposed By | | Date/Time | | | |